

# BITUMEN 80/100

CHARACTERISTIC	LIMIT	TEST METHOD
Penetration @25 °C, 0.1 mm, Min/Max	80/100	ASTM D 5
Flash Point , °C, Min	225	ASTM D 92
Solubility in TCE, %, Min	99	ASTM D 2042
Specific Gravity @25 °C	1.01-1.05	ASTM D 70
Ductility @25 °C, Cm, Min	100	ASTM D 113
Softening Point, °C, Min	42	ASTM D 36
Loss on Heating, %, Max	0.5	ASTM D 6
Drop in Penetration After Heating, %, Max	20	ASTM D 5 - D 6