

BITUMEN 40/50

CHARACTERISTIC	LIMIT	TEST METHOD
Penetration @25 °C, 0.1 mm, Min/Max	40/50	ASTM D 5
Flash Point , °C, Min	230	ASTM D 92
Solubility in TCE, %, Min	99.0	ASTM D 2042
Specific Gravity @25 °C	1.01-1.06	ASTM D 70
Ductility @25 °C, Cm, Min	100	ASTM D 113
Softening Point, °C, Min	49	ASTM D 36
Loss on Heating, %, Max	0.2	ASTM D 6
Drop in Penetration After Heating, %, Max	20	ASTM D 5 - D 6